

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2002-299110

(43)Date of publication of application : 11.10.2002

(51)Int.Cl. H01F 1/053

B22F 3/00

C22C 33/02

// C22C 38/00

(21)Application number : 2001-102491 (71)Applicant : TDK CORP


(22)Date of filing : 30.03.2001 (72)Inventor : KATO EIJI

ISHIZAKA TSUTOMU

NAKANE MAKOTO

(54) METHOD OF MANUFACTURING RARE-EARTH ELEMENT PERMANENT
MAGNET

BEST AVAILABLE COPY



(57)Abstract:

PROBLEM TO BE SOLVED: To provide a method by which a rare-earth element permanent magnet, that is superior in both coercive force and residual magnetic flux density can be manufactured.

SOLUTION: After a mixture of alloy X powder, composed mainly of R12T14B (where R1, T, and B respectively denote one or more kinds of rare earth elements including Y (Dy is indispensable), one or more kinds of transition metal elements, and boron) and alloy Y powder, composed mainly of R2T (where R2 and T respectively denote one or more kinds of heavy rare-earth elements and one or more kinds of

transition metal elements) is obtained, the mixed powder is sintered. The magnetic characteristics of the rare-earth permanent magnet can be improved, by adjusting the Dy ratio which is the ratio of the content of the heavy rare-earth elements in the alloy X powder to that of the heavy rare-earth elements in the sintered magnet composition to be 0.38-0.99 and R ratio, which is the ratio of the content of the rare-earth elements in the alloy X powder to that of the rare-earth elements, in the sintered magnet composition to be 0.94-1.03.

LEGAL STATUS

[Date of request for examination] 07.12.2004

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's

BEST AVAILABLE COPY

decision of rejection]

[Date of requesting appeal against
examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office

BEST AVAILABLE COPY